

Product Data Sheet Star Favorit and Star Favorit Superfront

FunderMax produces and supplies melamine-faced chipboards and melamine-faced MDF boards Star Favorit and Star Favorit Superfront according to the requirements of EN 14322:2017.

Deviations from the EN 14322:2017 standard concerning thickness tolerance apply to the below mentioned products:

Surface Texture	Board substrate	Thickness range [mm]	Star Favorit	Star Favorit Superfront
All except: SG, HG, real metal, PM	Chipboard P2, P3, P5, B1, MDF	8 to 20 > 20	-	± 0,5 + 0,5 / - 1,0
SG	Chipboard P2	≤ 20 > 20	± 0,5 + 0,5 / - 1,0	+ 0,5 / - 1,0
	MDF	15 to 20	+ 0,3 / - 0,8	+ 0,3 / - 0,8
HG, real metal	Chipboard P2	≤ 20 > 20	± 0,5 + 0,5 / - 1,0	+ 0,5 / - 1,0
PM	Chipboard P2	8 to 20 > 20 to 38	+ 0 / - 0,6 + 0 / - 0,7	
	Chipboard P3	18	+ 0 / - 0,6	-

Fire classification according to EN 13501-1:

Board substrate	End use condition	Thickness range [mm]	Star Favorit	Star Favorit Superfront
Chipboard P2, P3, P5 MDF	maximum 22 mm open air gap behind the wood-based panel	≥ 9	D-s2, d0	D-s2, d0
Chipboard P2, P3, P5 MDF	with open air gap behind the wood-based panel	≥ 18	D-s2, d0	D-s2, d0
Chipboard B1	No air gap behind the wood-based panel	12 to 38	B-s1, d0	B-s1, d0

Note:

This document has been drawn up to the best of our knowledge and with special diligence. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications can result from the continuous further development, as well as from changes in standards and documents originating from statutory bodies.